

AQUEOUS DISPERSION OF SILICONE RUBBER PARTICLE

Patent number: JP63309565
Publication date: 1988-12-16
Inventor: SHIMIZU KOJI; HAMADA MITSUO
Applicant: TORAY SILICONE CO
Classification:
- **international:** C09D3/82; C09D5/00; C10M107/50; C10M173/02;
C10N20/06; C10N40/00; C10N50/02
- **european:**
Application number: JP19870146681 19870612
Priority number(s): JP19870146681 19870612

Report a data error here

Abstract of JP63309565

PURPOSE: To obtain the title aqueous dispersion excellent in storage stability and useful as a mold release or a lubricant, by mixing water with silicone rubber particles of a specified average particle diameter and a surfactant. **CONSTITUTION:** Silicone rubber particles (B) of an average particle diameter of 0.1-1,000µm, preferably, 0.5-20µm are obtained by dispersing a liquid addition-curing silicone rubber composition (a) comprising an organopolysiloxane (i) having at least two alkenyl groups in the molecule, an organohydrogenpolysiloxane (ii) having at least two Si-bonded atoms in the molecule and a platinum compound catalyst (iii) in water (c) as fine particles in the presence of, optionally, a surfactant (b) and heating the formed dispersion. 100pts.wt. water (A) is mixed with 1-35pts.wt. component B and 0.05-10pts.wt. surfactant (C).

Data supplied from the esp@cenet database - Worldwide